PAPER • OPEN ACCESS

Exploiting asymmetric wire critical current for the reduction of AC loss in HTS coil windings

To cite this article: Zhenan Jiang et al 2019 J. Phys. Commun. 3 095017

View the article online for updates and enhancements.

Journal of Physics Communications

PAPER

2

3

OPEN ACCESS

CrossMark

RECEIVED 31 July 2019

REVISED

5 September 2019
ACCEPTED FOR PUBLICATION

13 September 2019

PUBLISHED 26 September 2019

Original content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence.

Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.



Exploiting asymmetric wire critical current for the reduction of AC loss in HTS coil windings

Zhenan Jiang¹⁽¹⁾, Natsumi Endo^{1,2}, Stuart C Wimbush¹, Justin Brooks¹⁽⁰⁾, Wenjuan Song^{1,3}, Rodney A Badcock¹⁽⁰⁾, Daisuke Miyagi⁴ and Makoto Tsuda²

¹ Robinson Research Institute, Victoria University of Wellington, Wellington 6140, New Zealand

Department of Electrical Engineering, Graduate School of Engineering, Tohoku University, Sendai 980-8579, Japan

School of Electrical Engineering, Beijing Jiaotong University, Beijing 100044, People's Republic of China

Department of Electrical and Electronic Engineering, Chiba University, Chiba 263-8522, Japan

E-mail: zhenan.jiang@vuw.ac.nz

Keywords: hybrid coil winding, HTS coils, asymmetric critical current, AC loss, REBCO

Abstract

Critical current and AC loss in coil windings are two important factors for various HTS applications. Many coated conductors exhibit asymmetry in the variation of the critical current with magnetic field angle. This asymmetry results in different coil critical current values depending on the orientation of the conductors in the coil windings. We report critical current and AC loss results at 77 K and 65 K for three hybrid coil assemblies which have a common central winding and different arrangements of the end windings. We found a difference greater than 13% in both the critical current and the AC loss results for the different arrangements. The results imply that if we wind coil assemblies smartly even using the same materials and the same design, we can not only improve critical current but also reduce AC loss significantly.

1. Introduction

REBCO-based coated conductors are steadily becoming the mainstream wire choice for HTS power applications such as transformers [1, 2], fault current limiters [3, 4], rotating machines [5] and fast-ramping magnets [6]. In such applications, the coated conductor wires are wound into HTS coils, and both the critical current, I_c , and the AC loss in the HTS coil winding are critical operational parameters.

Coated conductors exhibit asymmetry in the variation of their critical current with magnetic field angle [7, 8], $I_c(B, \pm \theta)$, where θ is the angle between the normal to the wide wire face and the magnetic field, B, perpendicular to the current flow direction as shown on figure 1. Figure 2 shows the measured asymmetric $I_c(B, \theta)$ dependence at 77 K of the 4 mm wide SuperPower SCS4050-AP wire used to form the end windings of the coil assemblies studied in this work. Previous research has shown that coil I_c can be improved by controlling the direction of the magnetic field relative to the coils in order to exploit the asymmetry in the wire I_c [9, 10]. On the other hand, efforts have also been made to obtain J_c values for calculating AC loss in HTS coils including using more than ten fitting parameters to describe the measured results [11] and eliminating the self-field effect by post-analysing measured data [12].

Furthermore, intensive AC loss analysis of HTS coils has been carried out both experimentally and numerically [14–20]. However, there has been no report to date on the influence of asymmetric wire critical current on coil AC loss. In this work, we explore the influence of wire I_c asymmetry on overall coil I_c as well as on the AC loss of hybrid coil assemblies [21–23].

The concept of hybrid coil assemblies arises due to the fact that conductors situated in different parts of a coil winding experience different magnetic field strengths and orientations, and therefore that using different conductors in the central and end parts of the coil can improve both the *I*_c and the AC loss of the overall coil [22] while simultaneously minimizing cost. Here, we go one step beyond this and consider improvements in performance that can be achieved simply by being aware of the relative orientations of the different windings as they are put together to form the coil assembly.





The question we seek to answer is: if hybrid coil assemblies are formed using the same coils but simply arranging the wire orientation in the different windings to take advantage of the inherent wire asymmetry, can we get not only increased I_c but also lowered AC loss in the overall assemblies?

2. Experimental methods

The coil assemblies studied comprise two end windings and one central winding as shown in figure 3. The end windings consist of one double pancake each while the central winding is formed from a stack of four double pancakes. The different windings are all wound with SuperPower SCS4050 AP wires with higher performance wire being selected for the end windings (104 A nominal 77 K self-field I_c compared to 86 A for the central windings) [24]. This highlights the benefit of hybrid coil assemblies in that maximal performance can be achieved using a cheaper wire for the bulk of the windings. Figure 4 shows the completed windings prior to assembly. HTS-110 Limited wound the coils with the superconductor layer facing the outside and maintaining the same wire orientation for each coil in the stack.

Three arrangements of the same set of coil windings have been constructed for this work: one arrangement is the same assembly featured in our previous work [23], where the detailed coil dimensions and construction method can be found. This we call the no-flipped assembly. In the second arrangement, the top end winding was turned upside-down leaving the central winding and the bottom end winding unchanged. This we call the one-flipped assembly. In the third arrangement, also the bottom end winding was turned upside-down to yield a configuration with both end windings reversed with respect to the original. This we call the both-flipped assembly.





Both the overall coil I_c and the AC loss of all three assemblies were measured and compared. The measurement method is described in detail in our previous work [22] and here we just recap the main points of the method. The coil assemblies were put in a foam-insulated liquid nitrogen dewar, the temperature of which is variable from 77 K to 65 K by reducing the pressure by pumping. Voltage taps were attached to the ends of the series windings for measuring both the I_c and the AC loss of the assemblies. Two Stanford Research Systems SR830 DSP Lock-in Amplifiers were used for AC loss data acquisition, one for registering the coil current and phase using a two-stage current transformer and the other for measuring voltage from the voltage taps. The I_c and AC loss measurements were carried out at both 77 K and 65 K.

3. Numerical methods

An axisymmetric 2D *H*-formulation finite element method simulation was carried out using COMSOL to calculate the expected AC loss of the coil assemblies [25]. Details of the simulation can be found in our previous work [26]. A combination of a structured mesh [27], edge elements [28], and a homogenization method [29] were used to reduce computing time. Figure 5 shows the structured mesh of the conductors forming the coil assemblies. Each pancake was divided into 40 elements along the axial direction and six sub-blocks in the radial direction.

For the central winding, the superconductor property is given as a non-linear *E-J* power law, $E = E_c (J/J_c (B))^n$, where $J_c (B)$ is the magnetic field-dependent critical current density, $E_c = 10^{-4}$ V m⁻¹, and n = 30. We adopted a modified Kim model [30] for the $J_c (B)$ relationship incorporating its angular dependence [31]:





Figure 6. Measured $I_c(B)$ curves (data points) and fitting curves (lines) in radial and axial magnetic fields for the SuperPower SCS4050-AP wire used to form the central winding of the hybrid coil assemblies.

$$J_c(B) = J_{c0} \left(1 + \frac{k^2 B_z^2 + B_r^2}{B_0^2} \right)^{-a}$$
(1)

where $B_0 = 41 \text{ mT}$, k = 0.41 and a = 0.24 are fitting parameters obtained from the measured $I_c(B)$ curves shown in figure 6 when the wire is exposed to a radial magnetic field, B_r , or an axial magnetic field, B_z . $I_c(B)$ is the integration of $J_c(B)$ over the cross-section of the superconductor. For the end windings, the measured asymmetric $I_c(B, \theta)$ dependence of the 104 A 4 mm wide SuperPower SCS4050 AP wire at 77 K (figure 2) was used.

Figure 7 shows a cross-section of the right side of the hybrid coil assembly superimposed on the field distribution resulting when the coil is energised with 40 A AC current. As shown on the figure, the inner and outer turns of the end windings are exposed to strongly differently oriented magnetic fields. We consider an inner turn in the top end winding as marked in red on the figure. If we define the upper edge of the turn as a reference for the wire orientation, then the field angle relative to the wire is α as shown on the right side of the figure. However, if we flip the upper end winding then the field angle will become $-\alpha$ for the coil turn in the same position because the wire reference edge is now the lower edge of the winding as illustrated on the far right of the figure. In the same way, we can consider the effect of flipping the end coils on the field orientations relative to the wire for each of the inner and outer turns in the top and bottom end windings, with the results shown on



Table 1. (B_{radial}, B_{axial}) components determined from the field angles in figure 7 for different coil arrangements.

	IIII	III	III	TT
		OL	LU	LL
Top end winding	$(B_{\rm r},B_{\rm z})$	$(B_{\rm r},B_{\rm z})$	$(B_{\rm r}, -B_{\rm z})$	$(B_{\rm r}, -B_{\rm z})$
Bottom end winding	$(-B_{\rm r},B_{\rm z})$	$(-B_{\rm r}, -B_{\rm z})$	$(-B_{\rm r},B_{\rm z})$	$(-B_{\rm r}, -B_{\rm z})$

the figure. The resulting field orientations for the inner turn are α , $-\alpha$, $180^{\circ} - \alpha$, and $-(180^{\circ} - \alpha)$ and for the outer turn $-\beta$, β , $-(180^{\circ} - \beta)$, and $180^{\circ} - \beta$.

Therefore, with fixed central windings, there are four possible values for the $I_c(B, \theta)$ properties of the end windings related to their wire orientation: upper reference edge for the top end winding and upper reference edge for the bottom end winding (denoted UU), upper edge for the top end winding and lower edge for the bottom end winding (UL), lower edge for the top end winding and upper edge for the bottom end winding (LU), and lower edge for the top end winding (LL).

If we assume $\alpha \approx 60^\circ$, then $-\alpha \approx -60^\circ$, $180^\circ - \alpha \approx 120^\circ$, and $-(180^\circ - \alpha) \approx -120^\circ$. If we look at figure 2, we see that the I_c value at -60° is greater than that at 60° , and the I_c value at 120° is greater than that at -120° . This implies that the LU assembly is most desirable in respect of the inner turns for a higher overall assembly I_c value. On the other hand, if we assume $\beta \approx 30^\circ$, then $-\beta \approx -30^\circ$, $180^\circ -\beta \approx -150^\circ$, and $-(180^\circ -\beta) \approx -150^\circ$. Again referring to figure 2, the I_c value at -30° is greater than that at 30° , and the I_c value at 150° is greater than that at -150° . This implies that the UL assembly is most desirable in respect of the outer turns, which is the opposite of the above. Therefore, the final I_c value of the coil assemblies depends largely on the local magnetic field throughout the assembly, and numerical simulation taking into account the measured $I_c(B, \theta)$ is necessary to predict the overall I_c value of coil assemblies.

For both critical current and AC loss simulations, we used $J_c(B, \theta)$ values deduced from the measured $I_c(B, \theta)$ shown in figure 2, by generating a three column look-up table $[B_{radial}, B_{axial}, J_c(B_{radial}, B_{axial})]$, where B_{radial} and B_{axial} are the radial and axial components of the magnetic field, and using the direct interpolation method [32]. If the field angle is α , $B_{radial} = B\cos(\alpha) = B_r$ and $B_{axial} = B\sin(\alpha) = B_z$ as shown in figure 1. The B_{radial} and B_{axial} components of the other field angles shown in figure 7 can be calculated in a similar way, resulting in the set of components shown in table 1 for the four different assemblies. AC loss values in the four different assemblies were calculated by using the different asymmetric $J_c(B_{radial}, B_{axial})$ values for the end windings in these four possible configurations.



Table 2. Measured and calculated coil assembly *I*_c values at 77 K and 65 K.

Assembly geometry	Measured coil I _c at 77 K (A)	Calculated coil I _c at 77 K (A)	Measured coil <i>I</i> _c at 65 K (A) 116.3	
No-flipped	54.9	52.0		
One-flipped	49.3	44.5	111.5	
Both-flipped	47.5	43.7	108.4	

Assembly $I_c(I_{c,coil})$ values can be determined from the following equation [13],

$$E_{ave} = \frac{\int_{S} E(t) \cdot dS}{S}.$$
 (2)

where E_{ave} is the average electrical field across the entire coil assembly cross section, S. $I_{\text{c,coil}}$ was defined when E_{ave} reaches 1 μ Vcm⁻¹.

4. Experimental and numerical results and discussion

4.1. Ic measurement of coil assemblies

Figure 8 shows the *E-I* curves of the three coil arrangements measured at 77 K and 65 K, after subtracting the voltage contribution resulting from the contact resistance between the double pancakes [22]. In this figure, the calculated *E-I* curves in the UU, UL, and LL assemblies are plotted together. The UU, UL, and LL assemblies correspond to the no-flipped, one-flipped, and both-flipped assemblies, as discussed later in section 4.2. Table 2 summarizes the different measured and calculated $I_{c,coil}$ values, determined at $E = 1 \,\mu$ Vcm⁻¹. At both temperatures, the I_c of the assemblies follows the trend of no-flipped > one-flipped > both-flipped. The measured I_c value of the no-flipped assembly is 16% higher than that of the both-flipped assembly at 77 K, and 7% higher at 65 K. The calculated $I_{c,coil}$ values can successfully predict the same tendency as the measurement even though the agreement between the measured and simulated results is not perfect. It is worth noting that the calculated E_{ave} values contain a linear component (slope) which we attribute to dynamic resistance which occurs when superconductors carry DC current under changing magnetic field [33]. Similar simulation results were observed in previous research [10]. The slope is related to the ramp rate, and a smaller ramp rate gives a gentler slope and hence smaller error for the $I_{c,coil}$ calculation. The existence of the slope is one of the reasons for the disagreement between the measured and simulated results. The results reconfirm the fact that coil assembly I_c values can be increased or decreased simply depending on how the wire is oriented in the coil windings.

4.2. AC loss measurement of coil assemblies

Figure 9 shows the measured AC loss values in the no-flipped assembly at 13.96 Hz, 19.80 Hz, and 26.62 Hz at 77 K and 65 K plotted as a function of the amplitude of the coil current, I_{coil} . The AC loss values obtained at different frequencies agree at both temperatures. This implies the AC loss in the assembly is hysteretic [22, 34]. Similar results (not shown) were obtained for the other two assemblies.





Figure 10 compares the normalised AC loss values in the three assemblies plotted as a function of I_{coil} normalised by the measured coil I_c values. As shown in the figure, the normalised AC loss values at the two temperatures are in very good agreement for all assemblies. This same result was observed in our previous works [21, 22]. The results re-confirm that AC loss in the coil assemblies can be scaled with the coil I_c values.

Figure 11 compares the measured AC loss values in the three different coil assemblies. The figures are plotted on a linear scale to observe the differences more clearly. At both temperatures, the AC loss of the assemblies follows the trend of no-flipped < one-flipped. This trend is opposite to the I_c result, i.e. the larger the I_c , the smaller the AC loss, consistent with the observation in our previous works [21, 22]. In other words, AC loss in hybrid coil assemblies can be reduced by increasing the assembly I_c , as the AC loss in coil



Figure 11. Comparison of measured AC loss in the three different coil assemblies at 19.80 Hz and (a) 77 K, (b) 65 K. In (a), simulation results for the LL and UU assemblies at 20 A, 30 A, and 40 A are marked.

Table 3. Simulated AC loss results for the four possible coil arrangements at four different currents, at 77 K. The reduction in AC loss of the LL configuration compared to the UU configuration is also shown.

		AC loss			
Coil current (A)	UU	UL	LU	LL	$(Q_{\rm UU} - Q_{\rm LL})/Q_{\rm UU}$ (%)
10.0	3.74e-3	3.63e-3	3.64e-3	3.53e-3	6
20.0	3.21e-2	3.08e-2	3.09e-2	2.96e-2	8
30.0	1.17e-1	1.11e-1	1.11e-1	1.05e-1	10
40.0	2.96e-1	2.80e-1	2.80e-1	2.63e-1	11

assemblies wound with REBCO wire increases with the 3rd to 4th power of I_t/I_c . The AC loss of the no-flipped assembly at 77 K is 13% lower than that of the both-flipped assembly at 40 A. The difference in the AC loss values of the assemblies at 65 K is even larger. This is the first demonstration that shows if we wind hybrid coils smartly using the same materials and the same design, we can not only improve I_c but also reduce the AC loss of the assembly.

Table 3 summarises the simulation results for the four possible coil arrangements at four different coil currents. Mimicking the experimental results, there is a systematic difference in the AC loss values for the different coil assemblies. For a given coil current, the AC loss in the LL assembly is the lowest and that in the UU assembly is the highest. The LU assembly and the UL assembly have approximately the same AC loss, between that of the LL and UU assemblies. As the coil current increases, the difference in AC loss also increases. The decrease in AC loss at 40 A is 11% which is close to the difference in the measured values for the no-flipped and both-flipped coil assemblies.

Figure 12 shows the radial magnetic field distribution in the end windings of the LL and UU assemblies (see enclosed with blue dashed lines) for a coil current of 40 A. Although the field distribution is broadly similar in the two arrangements, there is a clear difference between the two differently arranged end windings on the inner (left) side. The region of the end windings with high radial magnetic field component (red colour) is much greater in extent in the UU assembly than in the LL assembly. Because AC loss in coated conductors is determined by the perpendicular (radial) magnetic field component, this region is decisive in determining the overall AC loss of the coil [35]. This explains why the AC loss in the LL assembly is lower than that in the UU assembly.

A single wire orientation was maintained during winding of all the coils. Therefore, the no-flipped assembly which has the same wire orientation in both end windings must be either the UU assembly or the LL assembly.



Because the no-flipped assembly has the smallest measured AC loss and the LL assembly has the smallest calculated AC loss, we can easily conclude that the no-flipped assembly is the LL assembly. Then we can identify the both-flipped assembly as the UU assembly and note that its AC loss values are the largest. Finally, we can conclude that the one-flipped assembly is the UL assembly which has AC loss values between the UU and LL assemblies. In figure 11(a), the AC loss simulation results for the LL and UU assemblies taken from table 3 are compared with the experimental results. A reasonable agreement was obtained between the simulated and measured values. Therefore, the simulation result replicates the experimental result. E.g. the difference between the measured and simulated results at $I_{coil} = 30$ A for the LL is 2% and 11% respectively. The radial field distributions in figure 12 also explain why the no-flipped (LL) assembly has greater coil I_c than the both-flipped (UU) assembly, due to the lower radial (out-of-plane) fields present.

5. Conclusion

In this work, we have built three hybrid coil assemblies which have a common central winding and a different geometrical arrangement of the same end windings. The critical currents and AC losses of the assemblies were measured at both 77 K and 65 K. A 2D finite element method AC loss simulation of the assemblies at 77 K was carried out using *H*-formulation to provide insight into the experimental results.

We observed a notable difference in critical current of the different assemblies, even though the windings used the same materials and share the same design. At both 77 K and 65 K, the I_c of the assemblies followed the trend no-flipped > one-flipped > both-flipped. The measured I_c value of the no-flipped configuration was as much as 16% higher than the other configurations at 77 K. The results reconfirm the fact that coil assembly I_c values can be increased or decreased significantly depending on how the wires are oriented in the coil windings.

We also observed a substantial difference in AC loss values between the three coil assemblies. At both temperatures, the AC loss values of the assemblies followed the opposite trend to the I_c values, with higher I_c corresponding to lower AC loss. The reduction in the measured AC loss of the no-flipped configuration compared to the both-flipped configuration at 40 A, 77 K was 13%. According to the simulation, the variation in both AC loss and I_c in the different assemblies is due to the difference in the radial magnetic field in the inner part of the end windings.

This is the first demonstration that shows if we wind hybrid coil assemblies smartly even using the same materials and the same design, we can not only improve the overall critical current of the assembly but also reduce its AC loss.

Acknowledgments

This work was supported by the New Zealand Ministry of Business, Innovation and Employment Contract No. RTVU1707. The research was partially supported by the Japan Student Services Organization who provided a scholarship for N E to visit Victoria University of Wellington. Z J acknowledges the assistance of Gennady Sidorov in the development of the specialist cryostat used in this work.

ORCID iDs

Zhenan Jiang https://orcid.org/0000-0002-3482-3510

Justin Brooks (b) https://orcid.org/0000-0001-8586-776X Rodney A Badcock (b) https://orcid.org/0000-0003-0219-9570

References

- [1] Iwakuma M et al 2015 IEEE Trans. Appl. Supercond. 25 5500206
- [2] Pardo E, Staines M, Jiang Z and Glasson N 2015 Supercond. Sci. Technol. 28 114008
- [3] Didier G, Bonnard C H, Lubin T and Leveque J 2015 *Electr. Pow. Syst. Res.* **125** 150–8
- [4] Song W, Jiang Z, Staines M, Badcock R A and Jin F 2018 Supercond. Sci. Technol. 31 115001
- [5] Haran K S et al 2017 Supercond. Sci. Technol. **30** 123002
- [6] Park I, Lee C, Park J, Kim S and Jeong S 2017 IEEE Trans. Appl. Supercond. 27 4601105
- [7] Wimbush S C and Strickland N M 2017 IEEE Trans. Appl. Supercond. 27 8000105
- [8] Strickland N M, Wimbush S C, Rupich M W and Long N J 2019 IEEE Trans. Appl. Supercond. 29 8001304
- [9] Hong Z, Li W, Chen Y, Gömöry F, Frolek L, Zhang M and Sheng J 2018 *Physica C* 550 74–7
- [10] Zhang M, Kvitkovic J, Kim C H, Pamidi S V and Coombs T A 2013 J. Appl. Phys. 114 043901
- [11] Pardo E, Vojenčiak M, Gömöry F and Šouc J 2011 Supercond. Sci. Technol. 24 065007
- [12] Zermeno V M R, Habelok K, Stepien M and Grilli F 2017 Supercond. Sci. Technol. 30 034001
- [13] Ainslie M D, Bumby C W, Jiang Z, Toyomoto R and Amemiya N 2018 Supercond. Sci. Technol. 31 074003
- [14] Ainslie M D, Rodriguez-Zermeno V M, Hong Z, Yuan W, Flack T J and Coombs T A 2011 Supercond. Sci. Technol. 24 045005
- [15] Pardo E, Šouc J and Kováč J 2012 Supercond. Sci. Technol. 25 035003
- [16] Jiang Z, Long N J, Badcock R A, Staines M, Slade R A, Caplin A D and Amemiya N 2012 Supercond. Sci. Technol. 25 035002
- [17] Gömöry F, Šouc J, Pardo E, Seiler E, Soloviov M, Frolec L, Skarba M, Konopka P, Pekarčíková M and Janovec J 2013 IEEE Trans. Appl. Supercond. 23 5900406
- [18] Nguyen D N, Kim C H, Kim J H, Pamidi S and Ashworth S P 2013 Supercond. Sci. Technol. 26 095001
- [19] Zhang M, Yuan W, Kvitkovic J and Pamidi S 2015 Supercond. Sci. Technol. 28 115011
- [20] Queval L, Zermeno V M R and Grilli F 2016 Supercond. Sci. Technol. 29 024007
- [21] Jiang Z, Staines M, Long N J, Badcock R A, Bumby C W, Buckley R G, Song W and Amemiya N 2017 IEEE Trans. Appl. Supercond. 27 5900707
- [22] Jiang Z, Long NJ, Staines M, Badcock RA, Bumby CW, Buckley RG and Amemiya N 2016 Supercond. Sci. Technol. 29 095011
- [23] Sogabe Y, Jiang Z, Wimbush S C, Strickland N M, Staines M, Long N J and Amemiya N 2018 *IEEE Trans. Appl. Supercond.* **28** 4700105 [24] http://.superpower-inc.com/system/files/SP_2G+Wire+Spec+Sheet_for+web_2012FEC_v2_1.pdf
- [24] http:///superpower intecom/sistem/integor/conditional integor/conditional integor/condit
- [26] Song W, Jiang Z, Staines M, Badcock R A, Fang J, Sogabe Y and Amemiya N 2018 *Cryogenics* 94 14–21
- [27] Rodriguez-Zermeno V M, Mijatovic N, Traeholt C, Zirngibl T, Seiler E, Abrahamsen A B, Pedersen N F and Pedersen M P 2011 IEEE Trans. Appl. Supercond. 21 3273–6
- [28] Brambilla R, Grilli F and Martin L 2007 Supercond. Sci. Technol. 20 16–27
- [29] Zermeno V M, Abrahamsen A B, Mijatovic N, Jensen B B and Sørensen M P 2013 J. Appl. Phys. 114 173901
- [30] Kim Y B, Hempstead C F and Strnad A R 1962 Phys. Rev. Lett. 9 306–12
- [31] Song W, Fang J, Jiang Z, Staines M and Badcock R 2019 IEEE Trans. Appl. Supercond. 29 5501405
- [32] Hu D, Ainslie M D, Hampshire D P and Zou J 2016 IEEE Trans. Appl. Supercond. 26 6600906
- [33] Jiang Z, Toyomoto R, Amemiya N, Zhang X and Bumby CW 2017 Supercond. Sci. Technol. 30 03LT01
- [34] Banno N and Amemiya N 1999 Cryogenics 39 99–106
- [35] Amemiya N, Jiang Z, Iijima Y, Kakimoto K and Saitoh T 2017 Supercond. Sci. Technol. 17 983-8